

# Paintex AW

Highly alkaline, watter-free cleaning concentrate

## Properties

- Highly effective cleaning concentrate for alkali-sensitive surfaces
- especially for aluminum, zinc, non-ferrous metals
- Removes even highly cross-linked adhesions of all paint systems

## Application

Paintex AW is a water-free, highly effective cleaning concentrate that is mild to alkali-sensitive surfaces when used undiluted. When diluted with water, it is a highly alkaline cleaning concentrate for cleaning steel and stainless steel. In aqueous form, the cleaner is no longer suitable for aluminum, zinc and non-ferrous metals. Avoid adding water to Paintex AW, as this will cause corrosion on zinc, non-ferrous metal and aluminum surfaces.

Cleaning bath care

Care is recommended to maintain the cleaning effect of the used cleaning bath for as long as possible. More detailed information is available on request.

Suitable surfaces: Steel, stainless steel, non-ferrous metals, aluminum, galvanized components

Only treat after testing: Plastics

Not suitable surfaces: Ceramics

Area of application: closed spray and immersion applications

For the removal of: all paint systems, low to high degree of cross-linking

## Dosing

### Closed Spray Method; Closed Dipping Process

Concentration	100 %
Temperature	70 °C – 80 °C
Addition	RECOMMENDATIONS FOR ALUMINUM, ZINC AND NON-FERROUS METALS

### Closed Spray Method; Closed Dipping Process

Concentration	30 % – 50 %
Temperature	70 °C – 80 °C
Addition	RECOMMENDATIONS FOR HIGHLY ALKALINE CLEANING BATHS FOR STEEL AND STAINLESS STEEL

## Technical data

Density (20°C)	pH-value
1,16 kg / l	14

## Cleaning bath

Flashpoint	Appearance	pH-value
> 95 °C (Pensky-Martens DIN EN 22719-A)	2-phase; 1-phase in concentrate	13 - 14

### Notes

Store the product in its original container.

Storage should be frost-proof, although the solidified products can be used again after thawing without any loss of quality.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.