

Redulin BUR

Decolorizer

Properties

- for bleaching wool, silk, cotton, viscose and polyamide
- Achieves very intensive and stable whitening effects
- can also be used as a pre-spotting agent for color stains on white goods
- Can also be used as a stripper for dyed buttons (metal-free)

Application

Approximately 3 - 10 g Redulin Bur per liter of water is dissolved and heated to 30 - 50 °C. The material to be bleached should be constantly agitated during the treatment of about 20 minutes. After that, it is thoroughly rinsed. For cotton, the temperature can be 60 - 80 °C to improve the effect.

Note:

We recommend a hem test before using Redulin Bur on delicate garments and textiles with low color fastness. Use only stainless steel or plastic containers.

Caution:

Using Redulin Bur can irreversibly damage optical brighteners. Metals may darken during bleaching.

Technical data

pH-value	Bulk weight
10,0 ; 10 %	ca. 1200 kg / m ³

Notes

Store the product only in the original container, dry and protected from sunlight.
After removing partial quantities, the container should be resealed.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.